

Test Report P-BA 77/2017e

## **Determination of the Acoustic** Performance of a Wastewater **Installation System in the** Laboratory according to EN 14366

Institution for testing, supervision and certification, officially recognized by the building supervisory authority. Approvals of new building materials, components and types of construction

Director

Prof. Dr. Philip Leistner

Prof. Dr. Klaus Peter Sedlbauer

Client: Redi S.p.a.

Via Madonna dei Prati, 5/A

40069 Zola Predosa

Italy

Test object: Wastewater installation system consisting of plastic pipes and fittings

"PhonoBlack", OD 110 x 3.2, (manufacturer: Redi) with plastic pipe

clamps "Phonoklip" (manufacturer: Girpi).

Results sheet 1: Content:

Summary of test results Figures 1 to 3:

Figures 4 and 5:

Detailed results Test set-up

Annex A:

Measurement set-up, noise excitation, acoustic

parameters

Annex F:

Evaluation of measurements

Annex P:

Description of the test facility

Annex V:

Assessment according to VDI 4100

**Test date:** The measurement was carried out on April 24, 2017 in the test

facilities of the Fraunhofer Institute for Building Physics in Stuttgart.

Stuttgart, May 24, 2017

Responsible Test EnglisherUNG lead of Laboratory:

M.Sc. B. Kalt

Dipl.-Ing.(FH) S. Öhler

The test was carried out in a laboratory, accredited according to DIN EN ISO/IEC 17025:2005 by DAkkS. The accreditation certificate is D-PL-11140-11-01.

Any publication of this document in part is subject to written permission by the Fraunhofer Institute for Building Physics (IBP).

Fraunhofer-Institut für Bauphysik

Nobelstraße 12 · D-70569 Stuttgart Telefon +49 (0) 711/970-00 Telefax +49 (0) 711/970-3395 www.ibp.fraunhofer.de

Prüfstelle Bauakustik und Schallimmissionsschutz Nobelstraße 12 D-70569 Stuttgart Telefon +49(0) 711/970-3314; Fax -3406

akustik@ipb.fraunhofer.de www.ibp.fraunhofer.de/de/pruefstellen/bauakustik.html



## Determination of the Acoustic Performance of a Wastewater | P-BA 77/2017e **Installation System in the Laboratory**

Results sheet 1

Client:

Redi S.p.a., Via Madonna dei Prati 5/A, 40069 Zola Predosa, Italy

**Test specimen:** Wastewater installation system consisting of plastic pipes and fittings "PhonoBlack" (OD 110 x 3.2, manufacturer: Redi) with plastic pipe clamps "Phonoklip" (manufacturer: Girpi). (test object no.: 11064-2; see figure 4 and 5)

Test set-up:

- The pipe system was mounted according to figure 4 (see also Annex A).
- The system consisted of wastewater pipes (nominal size OD 110 x 3.2), three inlet tees (87.5°), two 45°-basement bends and a horizontal drain section. The inlet tees in the basement and in the ground floor were closed by lids. Plug connection of the pipes and fittings (shaped pipe sockets).
  - Pipe system: single layer pipes "PhonoBlack", material PVC modified with mineral filler, size OD 110, wall thickness 3.2 mm (3.3 mm, measured by IBP), weight 1.65 kg/m, density approx. 1.55-1.60 g/cm³ (1.5 g/cm³ measured by IBP).
  - Single layer fittings, material PVC, size OD 110, wall thickness 3.2 mm (3.3 mm measured by IBP), density 1,6 g/cm<sup>3</sup> measured by IBP.
  - Plastic pipe clamps "Phonoklip" 110 mm (manufacturer: Girpi) (see figure 5): In each storey (EG and UG) two clamps were installed, one in the lower and one in the upper wall area. Guide position in the upper wall area with red spacers an in the lower wall area the anchor position without spacers. The pipe clamps were fixed to the installation wall with dowels and thread rods.

The wastewater installation system was mounted by a technician under the authority of Fraunhofer IBP.

Test facility:

Installation test facility P12, mass per unit area of the installation wall: 220 kg/m², mass per unit area of the ceiling: 440 kg/m². Installation rooms: sub-basement (KG), basement (UG) front, ground floor (EG) front and top floor (DG), measuring rooms: UG front, UG rear (details in Annex P and EN 14366: 2005-02)

Test method:

FÖRDERUNG

The measurements were performed according to EN 14366; noise excitation by steady water flow with 0.5 l/s, 1.0 l/s, 2.0 l/s and 4.0 l/s. Additional evaluation for comparison with requirements following German standards DIN 4109-1:2016-07 and VDI 4100:2012-10 (details in Annexes A, F and V).

Result:

ı	"PhonoBlack" (OD 110 x 3.2, manufacturer: Redi) with plastic pipe clamps "Phonoklip" (manufacturer: Girpi)		Flow rate [l/s]			
			1.0	2.0	4.0	
	Airborne sound pressure level $L_{a,A}$ [dB(A)] according to EN 14366 for the basement test-room UG front	44	48	51	54	
	according to EN 14366 for the basement test-room  UG rear	< 10	< 10	13	19	
Ins fo	ofer Sound level LaFeq,n [dB(A)]  UG front	44	48	51	54	
	following DIN 4109 in the basement test-room  UG rear	< 10	13	17	22	
Inst. foll	Installation sound level $\overline{L_{AFeq,nT}}$ [dB(A)] UG front	42	45	49	52	
	following VDI 4100 in the basement test-room  UG rear	< 10	< 10	14	19	

Test date:

April 24, 2017

Notes:

- For comparing test results with requirements note Annex A.
- Sound levels below 10 dB(A) are not mentioned in the test report, since they are subject to an increased measurement uncertainty and moreover are not noticeable in a normal living environment.



The test was carried out in a laboratory, accredited according to DIN EN ISO/IEC 17025:2005 by DAkkS. The accreditation certificate is D-PL-11140-11-01.

Stuttgart, May 24, 2017 Head of Laboratory:

